



Chongqing JERI Marine Equipment Co.,Ltd.

Address: No 6, 24 floor, shimahe street, jiangbei, chongqing

Tel: +86-23-67023103; Mobile: +86-17723269020

E-mail: info@jeri-marine.com

<http://www.jeri-marine.com>

Self – polishing Antifouling Paint

Characteristics: antifouling for a long time, effectively prevent defile of bilge from barnacle、oyster、lime insects、bryozoan and algae etc. marine attaching organism, film surface can smooth in hydrolytic action, it can reached 100 um thickness in one spraying, good construction property.

Uses: mainly use for antifouling of hull waterline under part.

Technical target:

Mixing ratio: single component

Standard film thickness: Dry: 100μm/coat

Academic spreading rate: 0.28kg/ m²/100μm

Solid contents: 75%

Humidity requirement: below 85%

Drying time & Coating interval

Temperature (°C)	-10	0	10	20	30
Dry to touch (hrs)	60	50	40	30	20
Dry semi-hard (hrs)	12	8	6	5	4
Min. interval (hrs)	12	8	6	5	4

Substrate treatment:

The former coating ethylene linking paint must dry and no feculence

Matching

Applicable substrate:

Sprayed ethylene linking paint substrat