



Chongqing JERI Marine Equipment Co.,Ltd.

Address: No 6, 24 floor, shimahe street, jiangbei, chongqing

Tel: +86-23-67023103; Mobile: +86-17723269020

E-mail: info@jeri-marine.com

<http://www.jeri-marine.com>

Alcohol Acid Enamel Paint (different colors) (acquired the certification of classification society CCS)

Characteristics: good appearance and gloss retention property 、 good adhesion force 、 elements resistance、 construction property.

Uses: mainly use for steel facilities maintenance,also use for large steel structure 、 steel facilities 、 equipment、 pipeline anticorrosion, as a use of finish.

Technical target:

Mixing ratio: single component
Standard film thickness: Dry: 30 μ m/coat
Academic spreading rate: 0.09kg/ m²/30 μ m
Solid contents: 58%
Humidity requirement: below 85%
Drying time & Coating interval

Temperature ($^{\circ}$ C)	5	20	30
Dry to touch (hrs)	5	3	2
Dry semi-hard (hrs)	50	25	20
Min. interval (hrs)	50	25	20

Substrate treatment:

Primer surface should be clean and dry, no feculence

Matching :

Applicable under coatings: All primers